

10

20

25

30

35

[illegible]

according to Claim 5, wherein the peeling means is a material having a void layer in which a weight ratio of fine particles and a binder is 100:70 to 100:5.

5 7. The method of processing a light-sensitive material according to Claim 1, wherein a contacting time of the peeling means to the light-sensitive material is within 5 seconds.

*Copy C*  
10 8. The method of processing a light-sensitive material according to Claim 1, wherein a contacting time of the peeling means to the light-sensitive material is within 3 seconds.

15 9. The method of processing a light-sensitive material according to Claim 1, wherein the light-sensitive material is a light-sensitive material having a non-silver light-sensitive material.

20 10. The method of processing a light-sensitive material according to Claim 9, wherein the light-sensitive material is a lithographic printing plate having a non-silver light sensitive layer comprising a light-sensitive composition on an anodized support.

25 11. The method of processing a light-sensitive material according to Claim 1, wherein the light-sensitive material is a lithographic printing plate having a silver halide emulsion layer as a light-sensitive layer on an anodized aluminum support.

30 12. The method of processing a light-sensitive material according to Claim 11, wherein the development is a coating development in which a developing solution is coated onto the light-sensitive material to carry out the development.

35 13. The method of processing a light-sensitive material according to Claim 12, wherein the light-sensitive material

contains a hydrophilic colloid and the peeling means is brought into close contact with the light-sensitive material in the state that an amount of the developing solution per 1 g of the hydrophilic colloid is 50 ml or less.

5

~~14.~~ A method of making a lithographic printing plate which comprises exposing a lithographic printing plate having at least a silver halide emulsion layer on an anodized aluminum support and using a silver complex diffusion transfer process, coating a developing solution to effect development, bringing a peeling means into close contact with the lithographic printing plate and peeling at least the silver halide emulsion layer by the peeling means.

15 15. The method of making a lithographic printing plate according to Claim 14, wherein the silver halide emulsion layer comprises a hydrophilic colloid in an amount of 70% by weight or less based on the silver halide in terms of silver nitrate.

20 16. The method of making a lithographic printing plate according to Claim 14, wherein the lithographic printing plate further comprises a protective layer on the silver halide emulsion layer.

add C'